

TIB KAT[®] 223

TIB KAT 223 finds its use in the following applications and is suitable to replace **TIB KAT 226**:

- catalyst for 1 component MS Silyl systems
- catalyst for synthesis of polyurethan-systems
- catalyst for polycondensation reactions of RTV silicon resins and of silane terminated polymers

TIB KAT 223 is miscible with organic solvents, but sensitive to moisture.

TIB KAT 223 is available in special formulations upon request.

Product Data

Chemical description	Dioctyltindiketanoate
CAS No.	54068-28-9
Molecular weight	543.1 g/mol
Appearance	clear liquid

Specification

Tin content	≥ 19.0 %
Colour (Gardner)	≤ 5

Storage

TIB KAT 223 can be stored for at least one year if kept closed in the original packaging. Sensitive to humidity.

Packaging

200 kg drum and 1.000 kg ICB,
other packaging size upon request.

Special advice for security

Information concerning

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheet.

Customs Tariff No.: 2931 9000

Issue / Oct 16

TIB Chemicals AG | Mülheimer Strasse 16 -22 | D-68219 Mannheim | P.O. Box 81 02 20 | D-68202 Mannheim
Phone +49 (0) 621 8901- 811 | Fax +49 (0) 621 8901- 475 | info.@tib-chemicals.com | www.tib-chemicals.com

*This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give.
This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.*

