

## TIB KAT<sup>®</sup> 411

**TIB KAT 411** is a liquid catalyst based on DOT-softener compound.

**TIB KAT 411** can be applied for the curing of silicones and silane systems, especially for 1 k MS silyl polymer.

As **TIB KAT 411** is sensitive to hydrolysis, contact with moisture has to be minimized. Inertization of once opened drums with nitrogen is recommended.

---

### Product data

Formula	proprietary formulation
State of aggregation	liquid

---

### Specification

Tin content	9.5 – 10.5 %
Colour (Gardner)	≤ 5.0
Density (20°C)	0.960 – 1.030 g/ml

### Storage

**TIB KAT 411** can be stored at least one year if kept closed in the original packaging.

### Packaging

25 kg plastic drum,  
other packaging size upon request.

### Special advice for security

Information concerning

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheet.

**Customs Tariff No.: 38159090**

Issue 05/19

---

TIB Chemicals AG | Mülheimer Strasse 16 -22 | D-68219 Mannheim | P.O. Box 81 02 20 | D-68202 Mannheim  
Phone +49 (0) 621 8901- 811 | Fax +49 (0) 621 8901- 475 | info.@tib-chemicals.com | www.tib-chemicals.com

*This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give. This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.*

