

TIB KAT® 425 M60

TIB KAT 425 M60 is a liquid catalyst based on a dioctyltin oxide formulation.

TIB KAT 425 M60 can be applied for the curing of silicones and silane systems, especially for

- curing 1p MS Silyl systems
- curing of alkoxy based RTV-silicones
- curing of oxime based RTV-silicones.

TIB KAT 425 M60 is sensitive to hydrolysis and contact with moisture has to be minimized. Intertisation of once opened drums with nitrogen is recommended.

Product data

Description	DOT- blend
State of aggregation	liquid
Solubility	miscible with alcohols, hydrolysis in water

Specification

Tin content	13,5 – 14,5 %
Density (20°C)	1,090 – 1,098 g/cm ³

Storage

TIB KAT 425 M60 can be stored at least twelve months if kept closed in the original packaging. Material should be stored at temperatures above 15 degrees centigrade. Homogenization before use is recommended.

Packaging

50 kg plastic drum, 200 kg plastic drum, 1000 kg IBC, other packaging size upon request.

Special advice for security

Information concerning

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheet.

Customs Tariff No.: 3815 90 90

Issue 4 / 10/2021

TIB Chemicals AG | Mülheimer Strasse 16 -22 | D-68219 Mannheim | P.O. Box 81 02 20 | D-68202 Mannheim
Phone +49 (0) 621 8901- 811 | Fax +49 (0) 621 8901- 475 | info.@tib-chemicals.com | www.tib-chemicals.com



This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give. This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.
