

## TIB KAT<sup>®</sup> 617

**TIB KAT 617** is suitable for various applications in the catalysis of polyurethane systems. Compared to organotin catalysts TIB KAT 617 shows a lower activity offering longer pot life in 2p systems.

**TIB KAT 617** is especially useful in curing reactions at elevated temperatures and in curing systems based on aromatic isocyanates.

**TIB KAT 617** is typically used in concentrations between 0.02 - 1 wt.-% in relation to the total formulation.

Product Data	
Chemical formula	Zinc neodecanoate
State of aggregation	Colourless to yellowish liquid
Typical Data	
Zinc content	15.5 – 18.0 %
Density (20°C)	1.0 – 1.2 g/cm <sup>3</sup>

### Storage

**TIB KAT 617** can be stored for at least one year if kept closed in the original packaging and away from light and moisture.

### Packaging

200 kg drum, 25 kg drum  
other packaging size upon request.

### Special advice for security

Information concerning

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheet.

**Customs Tariff No.: 2931 90 00**

Issue / Aug 20

TIB Chemicals AG | Mülheimer Strasse 16 -22| D-68219 Mannheim| P.O. Box 81 02 20| D-68202 Mannheim  
Phone +49 (0) 621 8901- 811| Fax +49 (0) 621 8901- 475| info.@tib-chemicals.com| www.tib-chemicals.com

*This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give.  
This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.*

