

TIB KAT[®] 715

TIB KAT 715 is a liquid catalyst based on a blend of special metal carboxylates. The product is suitable to replace DBTL (**TIB KAT 218**) in certain polyurethane systems.

TIB KAT 715 is especially suitable for curing reactions at elevated temperatures.

TIB KAT 715 can be dissolved in common solvents for polyurethane systems, but it's recommended to test solution stability carefully.

TIB KAT 715 is typically used in concentrations between 0.02 - 0.5 wt.-%.

Product Data

Chemical formula	blend of Bismuth and Zinc based metal catalyst
State of aggregation	clear liquid

Specification

Metal content	≥ 15.0 %
Density (20°C)	approx. 1.1 g/cm ³
Colour (Gardner)	≤ 4

Storage

TIB KAT 715 can be stored for at least one year if kept closed in the original packaging and away from light and moisture.

Packaging

200 kg drum, 25 kg drum
other packaging size upon request.

Special advice for security

Information concerning

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheet.

Customs Tariff No.: 3815 90 90

Issue / Oct 16

TIB Chemicals AG | Mülheimer Strasse 16 -22 | D-68219 Mannheim | P.O. Box 81 02 20 | D-68202 Mannheim
Phone +49 (0) 621 8901- 811 | Fax +49 (0) 621 8901- 475 | info.@tib-chemicals.com | www.tib-chemicals.com

This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give. This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.

