

TIB KAT[®] 808

TIB KAT 808 is used as co-catalyst for the curing of unsaturated polyester resins.

TIB KAT 808 acts as polymerisation regulator in the cobalt-catalyzed crosslinking reaction.

Product Data

Chemical Formula	Cu-(OOC-R) ₂
Chemical name	Copper naphthenate
CAS No.	1338-02-9
Colour	dark green
Odour	typical solvent like
Non volatiles (150°C)	48 – 52 %
Flash point	> 62°C
Solubility	insoluble in water, soluble in solvents and oils

Specification

Copper content	7.7 – 8.5 %
Density (20°C)	0.92 – 1.00 g/cm ³

Storage

TIB KAT 808 can be stored for at least one year if kept closed in its original packaging at a cool and dry place.

Packaging

190 kg drum,
other packaging size upon request.

Special advice for security

Information concerning

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheet.

Customs Tariff No.: 3808 9210

Issue / Oct 16



TIB Chemicals AG | Mülheimer Strasse 16 -22 | D-68219 Mannheim | P.O. Box 81 02 20 | D-68202 Mannheim
Phone +49 (0) 621 8901- 811 | Fax +49 (0) 621 8901- 475 | info.@tib-chemicals.com | www.tib-chemicals.com

*This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give.
This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.*