

TIB KAT 811

TIB KAT 811 can be used as a primary drier, commonly in combination with auxiliary driers.

TIB KAT 811 promotes polymerisation and through drying and is especially suitable for coatings dried at low temperature and high humidity.

TIB KAT 811 is dilutable in common solvents like xylene or mineral spirits.

TIB KAT 811 should be used in concentrations between 0.1 – 0.3 wt.-% metal in relation to the total solid content.

Product data	
Chemical name	Cerium neodecanoate
CAS No.	68084-49-1
State of aggregation	liquid
Water content	≤ 0.5 %

Specification	
Cerium content	10.0 – 11.0 %
Density 20°C	1.000 – 1.100 g/ml

Storage

TIB KAT 811 can be stored for at least one year if kept closed in the original packaging.

Packaging

1000 kg IBC
 200 kg plastic barrels
 25 kg plastic drums
 other packaging size upon request.

Special advice for security

Information concerning:

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheets.

Customs Tariff No.: 3815 9090