

TIB KAT[®] 233S

TIB KAT 233S is applicable for following purposes:

- catalyst for manufacturing of polyurethanes
- catalyst for transesterification reactions
- catalyst for condensation reactions of RTV- silicone resins and of silanes
- catalyst for transesterification of polyacrylates.

TIB KAT 233S is slightly sensitive to moisture. In comparison to DBTA (**TIB KAT 233**) this compound shows higher catalytical activity in different application.

Product data

Chemical description	Modified Dibutyltindiacetate
CAS No.	1067-33-0 / 5967-09-9
Appearance	clear liquid

Specification

Tin content	32,5 - 34,0 %
Density (20 ⁰ C)	1,25 - 1,40 g/cm ³
Colour (Gardner)	≤ 5

Storage

TIB KAT 233S can be stored for at least one year if kept closed in the original packaging. Sensitive to frost and slightly sensitive to moisture.

Packaging

50 kg and 200 kg plastic drum, other packaging size upon request.

Special advice for security

Information concerning

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheet.

Customs Tariff No.: 3815 90 90

Issue / Oct 16

TIB Chemicals AG | Mülheimer Strasse 16 -22| D-68219 Mannheim| P.O. Box 81 02 20| D-68202 Mannheim
Phone +49 (0) 621 8901- 811| Fax +49 (0) 621 8901- 475| info.@tib-chemicals.com| www.tib-chemicals.com

*This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give.
This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.*

