

TIB KAT[®] 620

TIB KAT 620 is an effective catalyst for numerous applications.

TIB KAT 620 is especially useful in the following applications in the catalysis of polyurethane systems. Compared to organotin catalysts **TIB KAT 620** shows a lower reactivity offering longer pot life in 2p systems.

TIB KAT 620 should be used in concentrations between 0.02 – 0.2 wt.-% in relation to the total formulation.

Product Data

Chemical description	Zinc octoate
State of aggregation	clear liquid
Flash point	≥ 101°C

Specification

Zinc content	≥ 19.0 %
Density (20°C)	1.13 – 1.17 g/cm ³
Colour (Gardner)	≤ 4

Storage

TIB KAT 620 can be stored for at least one year if kept closed in the original packaging.

Packaging

200 kg drum,
other packaging size upon request.

Special advice for security

Information concerning

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheet.

Customs Tariff No.: 3815 90 90

Issue / Oct 16

TIB Chemicals AG | Mülheimer Strasse 16 -22 | D-68219 Mannheim | P.O. Box 81 02 20 | D-68202 Mannheim
Phone +49 (0) 621 8901- 811 | Fax +49 (0) 621 8901- 475 | info.@tib-chemicals.com | www.tib-chemicals.com

*This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give.
This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.*

