

## TIB KAT 728

**TIB KAT 728** is a liquid catalyst based on bismuth metal.

The product is suitable to replace DBTL (**TIB KAT 218**) in certain polyurethane systems.

**TIB KAT 728** can be dissolved in common solvents for polyurethane systems, but it's recommended to test solution stability carefully.

**TIB KAT 728** is typically used in concentrations between 0.01 - 0.1 wt.-%.

**TIB KAT 728** can be added to the reactants either as it is or blended with alcohols

**TIB KAT 728** is slightly sensitive to moisture.

---

### Product Data

Description	Bismuth carboxylate
Appearance	Clear liquid at RT /25°C

### Typical data

Metal content	26,5-29,0 %
Colour (Gardner)	≤ 15
Density (25°C)	1,200 – 1,400g/ml

### Storage

**TIB KAT 728** can be stored for at least half a year if kept closed in the original packaging. Sensitive to frost.

### Packaging

200 kg plastic drum, 1000kg IBC  
other packaging size upon request.

### Special advice for security

Information concerning

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheet.

**Customs Tariff No.: 38159090**

Issue 1 / Nov 2023

TIB Chemicals AG | Mülheimer Strasse 16 -22| D-68219 Mannheim| P.O. Box 81 02 20| D-68202 Mannheim  
Phone +49 (0) 621 8901- 811| Fax +49 (0) 621 8901- 475| info.@tib-chemicals.com| www.tib-chemicals.com

*This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give.  
This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.*

