

TIB KAT® 810

TIB KAT 810 can be used as a primary drier, commonly in combination with auxiliary driers.

TIB KAT 810 promotes polymerisation and through drying and is especially suitable for coatings dried at low temperature and high humidity.

TIB KAT 810 is dilutable in common solvents like xylene or mineral spirits.

TIB KAT 810 should be used in concentrations between 0.1 – 0.3 wt.-% metal in relation to the total solid content.

Product data

Chemical name	Cerium octoate
CAS No.	149-57-5 24593-34-8
State of aggregation	liquid
Water content	< 3%

Specification

Cerium content	9 - 11 %
----------------	----------

Storage

TIB KAT 810 can be stored for at least one year if kept closed in the original packaging.

Packaging

200 kg drums and 1.000 kg IBC,
Other packaging size upon request.

Special advice for security

Information concerning

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheet.

Customs Tariff No.: 2846 1000

Issue 02/19