

TIB KAT 812

TIB KAT 812 can be used as a primary drier, commonly in combination with auxiliary driers.

TIB KAT 812 promotes polymerisation and through drying and is especially suitable for coatings dried at low temperature and high humidity.

TIB KAT 812 is dilutable in common solvents like xylene or mineral spirits.

TIB KAT 812 should be used in concentrations between 0.1 – 0.3 wt.-% metal in relation to the total solid content.

Product data	
Chemical name	Cerium octoate
CAS No.	7435-02-1
State of aggregation	liquid
Water content	< 3 %
Specification	
Cerium content	11 -13 %

Storage

TIB KAT 812 can be stored for at least one year if kept closed in the original packaging.

Packaging

200 kg plastic drum and 1.000kg IBC,, other packaging size upon request.

Special advice for security

Information concerning:

- classification and labelling according to the regulations governing transport and hazardous chemicals
- protective measures for storage and handling
- safety measures in case of accident and fire
- toxicity and ecological effects

is given in our material safety data sheets.

Customs Tariff No.: 2846 1000

Issue /Oct 16